



# AmeriPolish® X-Link™ WB Surface Sealer



## X-Link™ WB Surface Sealer HIGH STRENGTH CROSS LINKING SEALER

PROFESSIONAL USE ONLY  
 PLEASE READ THE FLAMMABILITY WARNING



### ◆ PRODUCT DESCRIPTION

AmeriPolish® X-Link™ WB Surface Sealer is a sprayable, low VOC, fast drying water-based sealer designed to protect and beautify decorative concrete. X-Link™ may be used to seal concrete with no color or with other compatible color products. X-Link™ is water and chemical resistant.

### ◆ USES

AmeriPolish® X-Link™ can be used on interior or exterior masonry and concrete-type surfaces. Use on colored or uncolored, stamped or

### ◆ FEATURES

- Exterior and interior applications
- Penetrating and durable
- Satin Finish
- Non-Yellowing
- UV Resistant
- Fast application, 1 hr drying between coats
- Fast curing, 12 hours for foot traffic, 24 hours for heavy traffic
- Water-based
- Breathable
- Helps prevent black marks from chewing gum
- Can be applied to most cementitious surfaces, other unglazed stone, and masonry surfaces

exposed aggregate concrete, porous brick, natural and manufactured stone, stucco, slate, unglazed tile and flagstone.

### ◆ PRODUCT SPECIFICATIONS

Application:	Spray and AmeriPolish® Microfiber Pad
Appearance:	Milky liquid
VOC:	Compliant (<5g/l)
Shelf Life:	1 Year
Solvent:	Water Based

### ◆ PREPARATION

WARNING: People, property, vehicles, animals, plants, and all surfaces not intended to be sealed should be protected from the product, splash, overspray, and wind drift, using polyethylene sheeting or other proven protective material.

NEW CONCRETE MUST CURE FOR AT LEAST 28 DAYS BEFORE APPLICATION. For best results, perform a moisture content test on both newly-poured and existing slabs. Slabs with a moisture content 5 lbs per 1000 sf or less show best performance (ASTM F1869 calcium chloride test). High moisture levels may affect performance of color. Do not apply if concrete is frozen, dirty or has standing water. Hydrostatic pressure may affect sealer performance. Surface to be sealed must be completely clean. Remove efflorescence, oil dirt, wax, paints, sealers, and curing compounds; pressure washing and/or power scrub if necessary. AmeriPolish® Rejuvenating Cleaner is highly recommended to clean the surface. Recommended surface profile is a CSP1. Refer to ICRI Guideline NO. 03732 "Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, and Polymer Overlays." RINSE THOROUGHLY. Sprinkle with water to test: if water beads up, clean and test again. If acid etching is used to clean, soak the entire surface with water before applying the acid. Apply acid according to manufacturer's directions. Slab must then be thoroughly neutralized with a pH neutralizer such as ammonia, baking soda, or T.S.P. ; unneutralized

acid residue will prevent the sealer from penetrating. When acid stops fizzing, rinse with clean water. Apply neutralizer. Wait 10-15 minutes, then flush surface with clean water. Repeat rinsing and neutralizing. Allow surface to dry at least 24 hours; surface must be dry to touch.

### ◆ DILUTION AND COVERAGE

X-Link™ is shipped ready to use. On polished concrete floors, X-Link™ will cover approximately 2000 - 2500 sf / gal (49-60 m2 / L) for each application, depending on the porosity of the concrete. Test areas to determine appropriate application procedure and adjust application rate.

### ◆ APPLICATION

**Testing:** Prior to starting project, apply X-Link™ to sample area of each type of concrete to be treated, using applications procedures proposed for project. Confirm that concrete is receptive to sealer.

**Project Conditions:** Ambient temperature during application should be 55°F-80°F (12.8°C -26.7°C). Do not apply on rainy, foggy, or extremely humid days. Excess moisture may prevent sealer from drying properly.

**Equipment:** Apply X-Link™ using a low pressure sprayer fitted with a conical mist tip with 4.2 gal/hr flow at 40 psi, (15.9 L/hr at 275.8 kPa) and AmeriPolish® Microfiber pad or similar microfiber floor finish applicator pad.

**Application:** Apply 2-3 light and even coats. Multiple light applications are recommended.

### ◆ VOC COMPLIANCE

In addition, AmeriPolish® X-Link™ WB Surface Sealer offers VOC compliance with low VOC at <5g/L and is also compliant with national, state and district regulations:

- US Environmental Protection Agency
- California Air Resources Board SCM Districts\*
- South Coast Air Quality Management District\*
- Maricopa County, AZ
- Northeast Ozone Transport Commission

\*Before application, verify product conformance with local and state codes.

**AmeriPolish® X-Link™ WB Surface Sealer**

CAUTION: Do NOT back-roll or back-brush. . . If additional applications are desired, check that work surface is tack-free before proceeding. Clean sprayer immediately after application.

**◆ NEXT STEPS**

Foot traffic may be allowed on sealed surface after 12 hours. For heavy traffic, allow 24 hours curing.

**◆ MAINTENANCE**

Sealed surface should be inspected periodically for areas of thin or traffic-worn sealer, and sealer reapplied as needed. Normal traffic may

**◆ SAFETY PRECAUTIONS**

**WARNING – Before using or handling this material, read the Material Safety Data Sheet and Warranty. EYE, SKIN AND GASTRO-INTESTINAL TRACT AND RESPIRATORY TRACT IRRITANT. Avoid contact with eyes, skin and clothing. Avoid breathing vapors or mists generated by this product. Use appropriate eye protection, and chemical-resistant gloves. Material is not flammable, but if exposed to fire material may produce irritating vapors and toxic gases (e.g., carbon dioxides and peroxides). KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY.**

require reapplication of X-Link™ annually. Use Ameripolish® Rejuvenating Cleaner for long lasting protection.

**◆ STORAGE**

- Store dry and upright at 40-105F° (4 - 41C°)
- Keep product from freezing
- Keep out of reach of children
- Seal container after use.
- Do not mix with other chemicals

**◆ WARRANTY**

The information contained herein is believed to be reliable. This information is based on laboratory testing and results. Because of variations in methods, conditions and equipment, each user must test this product to make a judgment of performance. Applicator is responsible for testing material for effectiveness and performance. Manufacturer obligation is limited to the refund of purchase price or replacement of material if proven to be defective. Claims must be made in writing and received within one year from date of product sale to original buyer. Sole remedy shall be replacement of product proven defective.

**◆ FIRST AID**

**Ingestion: CALL PHYSICIAN OR POISON CONTROL CENTER FOR MOST CURRENT INFORMATION. If professional advice is not available, DO NOT INDUCE VOMITING. If victim is convulsing, maintain an open airway and obtain immediate medical attention.**

**Eye Contact: Rinse eyes under gently running water. Use sufficient force to open eyelids and then “roll” eyes while flushing. Flush for 15 minutes minimum. Seek medical attention if any adverse effect persists after rinsing.**


**Skin Contact: If adverse skin effects occur, discontinue use and flush contaminated area. Seek medical attention if adverse effect occurs after flushing.**

**Inhalation: Remove victim to fresh air. If necessary, use artificial respiration to support vital functions. If adverse effect continues after removal to fresh air seek medical attention.**

Product Name – Ameripolish® X-Link™ WB Surface Sealer			Product Name – Ameripolish® X-Link™ WB Surface Sealer		
Product #	Shipping Wt.	Container(s) RTU: Ready To Use	Product #	Volume (RTU)	Coverage Sq. ft.
APXL-1	10 lbs.	RTU – 1 Gal	APXL-1	1 Gal.	600 Min. – 800 Max.
APXL-5	50 lbs.	RTU – 5 Gal	APXL-5	5 Gal.	3,000 Min. – 4,000 Max
APXL-30	300 lbs.	RTU – 30 Gal	APXL-30	30 Gal.	18,000 Min. – 24,000 Max
APXL-55	550 lbs.	RTU – 55 Gal	APXL-55	55 Gal.	33,000 Min. – 44,000 Max
APXL-250	2500 lbs.	RTU – 250 Gal	APXL-250	250 Gal.	150,000 Min. – 200,000 Max

**DEGREE OF HAZARD**

- 4 = EXTREME
- 3 = HIGH
- 2 = MODERATE
- 1 = SLIGHT
- 0 = INSIGNIFICANT



AmeriPolish, Inc. 120 Commercial Ave., Lowell, AR 72745 USA  
Toll Free: 1.800.592.9320 Office: +1 479.725.0033 Fax: +1 479.725.0031  
info@ameripolish.com ◆ www.ameripolish.com